



Standard: **EN 1706 ALUMINIUM AND ALUMINIUM ALLOY CASTINGS**
EN 1676 ALUMINIUM ALLOYED INGOTS FOR REMELTING

Alloy Group: **Al Si 9 Cu**

Replaces: **DIN 226 A - Si 9 Cu 3**

Alloy Designation: **EN AB and AC 46200 - Al Si 8 Cu 3**

CHEMICAL COMPOSITION %

ALLOY		ELEMENTS												
		Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Pb	Sn	Ti	Individual Impurities	Global Impurities
EN AB 46200	min	7,5		2,0	0,15	0,15								
	max	9,5	0,7	3,5	0,65	0,55	-	0,35	1,2	0,25	0,15	0,20	0,05	0,25
DIN 226 A	min	8,0		2,00	0,15	0,15								
	max	11,0	0,80	3,50	0,5	0,55	-	0,35	1,20	0,25	0,15	0,15	0,05	0,25

MECHANICAL FEATURES DETECTED FROM SEPARATE CASTING TEST SPECIMENS

Casting Process	Temper Designations	Rm Tensile Strenght		Sp 0,2 Proof Stress		A Elongation		HB Brinell Hardness	
		EN 1706 Mpa	DIN 1725 N/mm2	EN 1706 Mpa	DIN 1725 N/mm2	EN 1706 %	DIN 1725 %	EN 1706 HBW	DIN 1725 HB
SAND (as cast)	F	150	160-200	90	100-150	1	1-3	60	65-90
CHILL (as cast)	F	170	180-240	100	110-160	1	1-3	75	70-110
PRESSURE DIE (as cast)	F	240		140		1		80	

Karaağaç OSB Mh. Eskibağlar Cd. No: 9/1 Kapaklı / Tekirdağ

+90 212 875 22 22

satis@gkrmesek.com

www.gkrmesek.com